



C/Estación s /n
 17457-Riudellots de la Selva (Girona-Spain)
 Teléfono: 972.47.76.00 – Fax: 972.47.76.10
 N.I.F.: A-17.003344
 E-mail: acebsa@acebsa.es / Web: acebsa.com

SPECIFICATIONS

| “IBERFIL H or HC G2 1 C/V ” | | | |
|--|--|-----------------|-----------------|
| SPECIFICATIONS: | | | |
| Basecoat | Enameled with polyester-imide | | |
| Overcoat | Polyamide-imide (<i>Optional</i>) | | |
| Insulation | Glass-fibers wound resin or varnish impregnated | | |
| Numbers of layers | 1 | | |
| Thermal index | 155 | 180 | 200 |
| Correspondence specifications: IEC- | 60317-48 | 60317-49 | 60317-50 |
| UNE-EN- | 60317-48 | 60317-49 | 60317-50 |
| Elongation at break | 20 % | | |
| Breakdown voltage | > 1260 V | | |
| Adhesion | Min. 10 x diameter | | |
| Production range | 1<diameter<6 mm | | |
| CORRESPONDENCE SPECIFICATIONS: | | | |
| IEC- | 60.317-0-6 | | |



C/Estación s /n
 17457-Riudellots de la Selva (Girona-Spain)
 Teléfono: 972.47.76.00 – Fax: 972.47.76.10
 N.I.F.: A-17.003344
 E-mail: acebsa@acebsa.es / Web: acebsa.com

SPECIFICATIONS

| “IBERFIL H or HC G2 2 C/V ” | | | |
|--|--|-----------------|-----------------|
| SPECIFICATIONS: | | | |
| Basecoat | Enameled with polyester-imide | | |
| Overcoat | Polyamide-imide (<i>Optional</i>) | | |
| Insulation | Glass-fibers wound resin or varnish impregnated | | |
| Numbers of layers | 2 | | |
| Thermal index | 155 | 180 | 200 |
| Correspondence specifications: IEC- | 60317-48 | 60317-49 | 60317-50 |
| UNE-EN- | 60317-48 | 60317-49 | 60317-50 |
| Elongation at break | 20 % | | |
| Breakdown voltage | > 1500 V | | |
| Adhesion | Min. 10 x diameter | | |
| Production range | 1<diameter<6 mm | | |
| CORRESPONDENCE SPECIFICATIONS: | | | |
| IEC- | 60.317-0-6 | | |